



# GreatFloor 200

## Epoxy Coating for Concrete Floors



### PRODUCT DESCRIPTION

Pioneer Pro GreatFloor 200 is a two component polyamide epoxy compound which cures into a tough and hard film.

### Key Features

- Semi – gloss
- High Durability
- Good chemical, solvent and abrasion resistance
- Very good adhesion on steel, concrete, and broadcast aggregate

### Product Specifications / Typical Properties / Physical Characteristics

Table 1:  
Physical Properties: UNCURED STATE\*

Parameters	Result
Color	Standard colors and customized color
Components	2
Mixing Ratio (Part A: Part B)	3:1 by volume
Induction Time	20-30 mins
Appearance of Applied	No surface Defects
%solid by weight (mixed)	60-80
Density, g/mL Part A Part B	1.20 - 1.40 0.88 – 0.92
Fineness of Grind (FOG), NS	
Viscosity @ 29° C	4-6 hrs (less at higher temperature)
Drying Time Initial Cure @ 29°C Full Cure	12 hrs 168 hrs

## Applications

It is ideally recommended as finishing coat for the following:

1. For properly prepared and primed steel and metal structure and equipment.
2. Floor coating over concrete epoxy primer.
3. Finish coat over broadcast aggregate, slurry and trowelled epoxy systems.

**Table 2.**

### Physical Properties: CURED STATE\*

Parameters	Results
Opacity, 150 microns wft	95% min
Gloss	>90
Adhesion, 7days curing	4B-5B
Hardness, 7 days curing	H min
Flexibility (Mandrel Test)	No crack at 180° bent
Abbrasion Resistance test, mg (1,000 cycles)	35 mg (weight loss)
QUV, 200 hrs (ASTM G154 Cycle 1)	No cracking, no blistering, no chalking
Theoretical Coverage @ 50m DFT	7-10 m <sup>2</sup> /L

**Table 3. Chemical Properties:**

Parameters	Results
VOC, g/L	
Part A	298.2
Part B	405.1

## Application Procedure

### Surface Preparation

**Aged Uncoated Concrete.** Must be dry, clean and free from oils, fats or greases. Degrease or scrub with detergents if necessary. The concrete must be free from any incompatible additives or curing agents. Acid etch or abrasive blast clean. Prime with Pioneer Pro GreatFloor 100'

**Previously Epoxy-Coated Concrete.** Remove loose dirt, dust and paint by sweeping or vacuum cleaning. Remove grease, oil, floor compound wax and other contaminants. Caustic soda treatment must be used on areas covered with a built-up grease and / or soap scum. Heavy contaminated areas may require further removal by mechanical methods. If the floor is very old and completely saturated with oil, no cleaning method will completely remove the oil. In this case, try small areas and apply a sample of the system before cleaning the entire floor. Very glossy or hard coatings should be lightly sanded to insure maximum adhesion. Concrete floor areas which require patching should be free of dirt, oil, grease and other chemical contaminants. A test patch is recommended for use over existing coatings. Prime with Pioneer Pro GreatFloor 100.

**Steel.** Remove all loose rust, dirt, moisture, grease or other contaminants from surface. Power-tool clean SSPC-SP3 or hand tool clean SSPC-SP2. For more severe environments, dry abrasive blast SSPC-SP7. Water blasting is also acceptable. Prime with Pioneer Steel Primer.

### Method

1. Flush all equipment with thinner before use.

2. Stir each component separately, then mix Part B (Hardener) into Part A (Resin) in 3:1 ratio (Part A: Part B). Mix until homogenous. Let stand for 20-30 minutes before application.
3. Apply a wet coat in even, parallel passes. Overlap each pass 50% to avoid bare areas and pinholes. If required, cross spray at right angles to first pass.
4. Check dry film thickness using non-destructive dry film thickness gauge such as Mikrotest or Elcometer. If less than the specified thickness, apply additional material.
5. Touch up random pinholes and small damaged or bare areas by brush when film is dry to touch. Larger areas by brush when film is dry to touch. Larger areas should be resprayed.
6. Clean all tools or equipment used while coating is still in its uncured state. Use Pioneer Epoxy Reducer or lacquer thinner to clean tools and spills.

**Cleaning.** Clean all tools or equipment used while coating is still in its uncured state. Use lacquer thinner to clean tools and spills.

### **Application Equipment**

The following is a guide; suitable equipment from other manufacturers may be used. Changes in pressure, hose and tip size may be needed for proper spray characteristics.

**Conventional Spray** - Industrial equipment such as De Vilbiss, MBC or JGA, or Binks #18 or 62 spray gun. A moisture and oil trap in the main air supply, mechanical pot agitator, separate regulators for air and fluid pressure are recommended.

**Airless Spray** – Standard equipment such as a 33:1 pump or larger with a 0.017-inch tip with pre-orifice or fine finish tip.

### **Packaging**

Gallon set (4 sets per box)

### **Storage**

12 months in an unopened bag from date of manufacturing following the required storage conditions.

### **Shelf Life**

24 months

### **Health and Safety Precautions**

Read safety data sheet before use. Safety precautions must be strictly followed during storage, handling and use.

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. Use only in well-ventilated areas. Store in cool, dry place in tightly closed receptacles. Vapors are heavier than air and may spread along floors. Vapors may form explosive concentration of vapors in air and avoid vapor concentrations higher than the occupational exposure limit. Avoid inhalation of vapour, dust and spray mist. Avoid inhalation of vapour, dust and spray mist. Avoid contact with skin and eyes. Eating, drinking and smoking should be prohibited in area where the material is handled, stored and processed.

Avoid storage near extreme heat, ignition sources or open flame. Keep container tightly sealed. Store in an area with adequate ventilation.

## **KEEP OUT OF REACH OF CHILDREN**

### **Warranty and Disclaimers**

Unless an additional warranty is specifically stated on the applicable product literature, Pioneer warrants that each Pioneer product conforms with the applicable Pioneer product specification at the time of shipment, and when properly used and maintained in accordance with Pioneer's current published Technical Data Sheet (TDS), will serve the purpose for which it is intended. The recommendations and statements in Pioneer's TDS are based on good building practice but are not, by any means, an exhaustive statement of all relevant information. Pioneer shall not be liable for the recommendations in its TDS and the performance of the relevant Product. Pioneer shall also not be liable for any claims, damages or defects arising from, or in any way attributable to poor workmanship, incorrect design or detailing, use of the Pioneer product in unsuitable conditions, and force majeure.

Pioneer MAKES NO OTHER WARRANTIES, CONDITIONS OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOMER OR USAGE OF TRADE. If the Pioneer Product does not conform to this warranty, then the sole and exclusive remedy is, at Pioneer's option, the replacement of the Pioneer product or refund of the purchase price.

### **Limited Liability**

Except where prohibited by law, Pioneer will not be liable for any loss or damage arising from the use or application of the Pioneer product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.